



AFA N2 - LDPE

Color: cloudy nature, homogen

MFI*: 1,0-1,5

Density: appr. 0,92 g/cm³

Moisture: <0,05 %

Filtration: 80 μ



AFA T3A - LDPE

Color: light greenish/grey translucent, homogen

MFI*: 0,8-0,9

Density: appr. 0,95 g/cm³

Moisture: <0,05 %

Filtration: 90 μ



AFA T3C - LDPE

Color: light greenish/dark translucent, homogen

MFI*: 0,8-0,9

Density: appr. 0,95 g/cm³

Moisture: <0,05 %

Filtration: 100 μ



AFA B2 - LDPE

Color: dark grey, homogen

MFI*: 0,3-0,4

Density: appr. 0,94 g/cm³

Moisture: <0,03 %

Filtration: 90 μ



AFA B3 - LDPE

Color: dark grey, homogen

MFI*: 0,4-0,6

Density: appr. 0,94 g/cm³

Moisture: <0,03 %

Filtration: 100 μ



Marvin Mensing

Tel. +49(0) 4871 7080 351

Mobil: +49(0) 151 1886 1573

marvin.mensing@afa-nord.de

AFA Nord GmbH

Böternhöfen 13

24594 Hohenwestedt

www.afa-nord.de

AFA
NORD GmbH

Agrarfolienaufbereitung

AFA B3C - LDPE

Color: dark grey, homogen

MFI*: 0,5-0,8

Density: appr. 0,95 g/cm³

Moisture: <0,05 %

Filtration: 100 µ



AFA SW2 - LLDPE

Color: beige/white, homogen

MFI*: 0,9-1,4

Density: appr. 0,93 g/cm³

Moisture: <0,05 %

Filtration: 90 µ



AFA SG2 - LLDPE

Color: green, homogen

MFI*: 1,0-1,5

Density: appr. 0,93 g/cm³

Moisture: <0,05 %

Filtration: 90 µ



The low PP content of < 1% and an Charpy impact of at least 60 KJ/m² characterize our LDPE granules for the production of high-quality hard-plastics products. For this we can offer other products, for example AFA B5.

AFA B5 - LDPE

Color: dark grey, homogen

Charpy impact: >60KJ/m²

Density: appr. 0,95 g/cm³

Moisture: <0,05 %

Filtration: 400µ



Marvin Mensing

Tel. +49(0) 4871 7080 351

Mobil: +49(0) 151 1886 1573

marvin.mensing@afa-nord.de

AFA Nord GmbH

Böternhöfen 13

24594 Hohenwestedt

www.afa-nord.de